



Ultimate Grip Primer

ROCATEX Ultimate Grip Primer is a solvent-free, rapid drying, one coat bonding primer with adhesion enhancing additives. Designed to adhere to even the most problematic non-absorbent surfaces, the rough textured finish promotes maximum bonding when tiling, levelling, screeding and rendering.

- **Multi-Purpose / Ready-To-Use**
- **Ultimate Bond / Textured 'Key Coat' Finish**
- **Rapid Drying / One Coat Application**
- **Very Low Emissions / EC1 Plus (VOC)**
- **Non-Absorbent / Absorbent Surfaces**
- **Existing Tiles / Asphalt / Bitumen**
- **Concrete / Blockwork / Screeds / Timber**
- **Interior / Exterior / Domestic / Commercial**

DESCRIPTION

ROCATEX Ultimate Grip Primer is a solvent-free, rapid drying, one coat bonding primer with adhesion enhancing additives. Designed to adhere to even the most problematic non-absorbent surfaces, the rough textured finish promotes maximum bonding when tiling, levelling, screeding and rendering.

Suitable for interior and exterior use and for non-absorbent and absorbent substrates including; existing tiles, asphalt, bitumen, metal, glass, moisture resistant chipboard, lime and gypsum plaster, plaster boards, concrete, screeds, anhydrite, levelling compounds, cement based rendering and wooden surfaces such as plywood and floorboards.

SUBSTRATE PREPARATION

All surfaces must be clean, firm, dry, free from all loose matter including dust, dirt, oil, grease, laitance and any other contaminants that may affect adhesion. Residual moisture content should not exceed the following values; Cement - 2%, Anhydrite - 0.5%, Heated Anhydrite - 0.3%, Gypsum Plaster - 1% (measured with CM instrument).

APPLICATION

Stir well prior to use. ROCATEX Ultimate Grip Primer should be used undiluted on non-absorbent surfaces and diluted 1:1 with clean water on absorbent surfaces. Apply evenly with a roller, brush or sponge. Do not over apply as this can cause the primer to form a skin, only a thin coat should be applied. The primer should not be applied to substrates with a temperature of less than 5°C or above 25°C. Please note that anhydrite requires two diluted coats.

On non-absorbent surfaces and anhydrite, the primer should be fully dry before next works can commence. Typically this will take between 15-60 minutes. The primer has to have fully dried prior to covering. In cases where the substrate is highly absorbent, additional coat(s) may be required.

The following information provides details for priming various common substrates. Unless stated otherwise, any reference to the term "diluted" means 1 part primer mixed with 1 part clean water.

ROCATEX

Rocatex Ltd
Camwal Park
Camwal Road
Harrogate, HG1 4PT

T: +44 (0)1423 882 990
F: +44 (0)1423 299 040
E: info@rocatex.com
www.rocatex.com

This information is offered without guarantee. The material should be used so as to take account of the local conditions and the surfaces to be treated. In case of doubt, the product should be tried out in an inconspicuous area.

Existing Tiles & Other Non-Porous Substrates - Apply 1 neat coat of ROCATEX Ultimate Grip Primer.
Metal - Apply 1 neat coat of ROCATEX Ultimate Grip Primer.

Flooring Grade Asphalt/Bitumen - Ensure the surface is in good condition and there are no signs of debonding and/or hollowness. Apply 1 neat coat of ROCATEX Ultimate Grip Primer.

Epoxy Damp Proof Membranes - Apply 1 neat coat of ROCATEX Ultimate Grip Primer.

Gypsum Plaster - The surface should be roughened up using a wire brush or other abrasive tool as this will remove the surface laitance. Ensure surface is clean and free from loose matter and apply 1 diluted coat of ROCATEX Ultimate Grip Primer. Substrate curing before tiling can commence is approximately 4 weeks.

Plaster Boards - Apply 1 diluted coat of ROCATEX Ultimate Grip Primer.

Concrete Screeds - Apply 1 diluted coat of ROCATEX Ultimate Grip Primer. Substrate curing before tiling can commence is approximately 6 weeks.

Power Floated Concrete - Once cured, power floated concrete should be mechanically abraded (scabbled or shot blasted) to remove any curing agents and open up the surface, followed by vacuum cleaning to remove any loose material, then apply 1 diluted coat of ROCATEX Ultimate Grip Primer.

Sand & Cement Screeds - Apply 1 diluted coat of ROCATEX Ultimate Grip Primer. Substrate curing before tiling can commence is approximately 3 weeks.

Anhydrite Screeds - The substrate must not leach moisture. Anhydrite screeds must not have a moisture content greater than 0.5% or 0.3% when part of a heating system. This can easily be tested by taking moisture readings across the whole surface. It is essential that surface laitance is removed in accordance with the screed manufacturer's recommendations, followed by vacuum cleaning to remove any loose material, then apply 2 diluted coats of ROCATEX Ultimate Grip Primer.

Plywood - Apply 1 diluted coat of ROCATEX Ultimate Grip Primer.

Tongue & Groove Boards/Floorboards - Apply 1 diluted coat of ROCATEX Ultimate Grip Primer.

Cement Based Tile Backer Boards - Priming prior to tiling is not required if the surface is clean and free from all loose matter. Please note that when applying a levelling compound, prime with 1 diluted coat of ROCATEX Ultimate Grip Primer.

COVERAGE

Non-Absorbent Surfaces (neat): Approx. 20m² per kg

Absorbent Surfaces (diluted): Approx. 10m² per kg

Depending on the absorbency and nature of the substrate, coverage and drying times will vary.

ROCATEX

Rocatex Ltd
Camwal Park
Camwal Road
Harrogate, HG1 4PT

T: +44 (0)1423 882 990
F: +44 (0)1423 299 040
E: info@rocatex.com
www.rocatex.com

This information is offered without guarantee. The material should be used so as to take account of the local conditions and the surfaces to be treated. In case of doubt, the product should be tried out in an inconspicuous area.

STORAGE

Store unopened, clear of the ground in a cool, dry, frost free environment. Shelf life is 12 months from date of manufacture. A small amount of liquid may form on the surface of the material, this can be readily remixed by stirring. If the container is left open for a period of time a skin will form over the material. This skin should be removed and not mixed into the product.

TECHNICAL DATA

Form:	Ready to use liquid
Colour:	Violet
Density:	1.3 g/cm ³
pH:	8
Viscosity:	2000 mPa.s
Solids Content:	67%
Drying Time:	15 to 60 minutes
Application Temp. Range:	5°C to 25°C
Service Temp. Range:	-20°C to 80°C
Shelf Life:	Up to 12 months when stored in unopened containers, under cool dry conditions. Avoid frost.